

TRÈS BN[®]

Boron Nitride Cosmetic Powders



Pressed Powder Eyeshadow with PUHP3050

A dramatic, deep brown with subtle shimmer created by 50 um boron nitride platelets

| <u>Ingredient (Supplier)</u> | <u>INCI Name</u> | <u>%</u> |
|--------------------------------|--------------------------------|------------------------|
| Talc (D90 <10µm) | Talc | 51.20 |
| Zinc Stearate USP | Zinc Stearate | 5.00 |
| Orgasol 2002D Nat Cos (Arkema) | Nylon-12 | 3.00 |
| Microcel E (World Minerals) | Calcium Silicate | 1.00 |
| Yellow Iron Oxide | Iron Oxides/CI 77492 | 5.00 |
| Red Iron Oxide | Iron Oxides/CI 77491 | 5.00 |
| Black Iron Oxide | Iron Oxides/CI 77499 | 14.00 |
| Methyl Paraben | | 0.20 |
| Propyl Paraben | | 0.10 |
| Dermol 20 SS (Alzo) | Octyldodecyl Stearoyl Stearate | 3.00 |
| Dermol 2014 (Alzo) | Octyldodecyl Myristate | 1.50 |
| DC 200 Fluid/100 cs | Dimethicone | 1.00 |
| PUHP3050 | Boron Nitride | <u>10.00</u> 100.00 |

Notes: In the EU, colors are listed by CI #.

The talc used was a fine, platy talc, 90% of the particles are under 15 µm.

Zinc Stearate is USP grade

Manufacturing Procedure: Combine dry ingredients. Mill until color is dispersed. Spray on oil with high intensity agitation. Add PUHP3050 mixing thoroughly with gentle agitation. Press into pans.

Formulation – SGPES3050



USA:

Saint-Gobain Advanced Ceramics

Boron Nitride Products
168 Creekside Drive
Amherst, NY 14228-2027
Tel: (716) 691-2052
www.BN.saint-gobain.com

EUROPE:

Saint-Gobain Solcera
Z.I. No. 1 Rue l'Industrie
27025 Evreux, Cedex
FRANCE
Tel: 33 (0)2 32 29 42 00

www.solcera.saint-gobain.com

www.TRESBN.com

The information, recommendations and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.


SAINT-GOBAIN
CERAMICS